

AMENDMENTS TO THE CLAIMS

1. **(Currently Amended)** Coating composition comprising:
 one or more thiol compounds;
 one or more oxidatively drying polyunsaturated condensation products of one or more fatty acids and/or esters, one or more polyols and ~~optionally~~ one or more polycarboxylic acids and/or anhydrides of polycarboxylic acids and optionally other building blocks;
 and one or more photo-initiators.

2. **(Previously Presented)** Coating composition according to claim 1, wherein the ratio between the number of unsaturated groups and the number of SH-functional groups is at least 1.5:1.

3. **(Previously Presented)** Coating composition according to claim 1, wherein the coating composition comprises 1-30 wt % of thiol compounds, related to the total weight of solid resin.

4. **(Previously Presented)** Coating composition according claim 1, wherein one or more isocyanates are used as building blocks for the oxidatively drying polyunsaturated condensation products.

5. **(Previously Presented)** Coating composition according to claim 1, wherein the coating composition is a high solids coating composition, comprising 0–40 wt.% solvents.

6. **(Previously Presented)** Coating composition according to claim 1, wherein the composition is an aqueous coating composition.

7. **(Previously Presented)** Coating composition according to claim 1, wherein the photoinitiator is active by visible light.

8. **(Previously Presented)** Coating composition according to claim 1, wherein the photoinitiator is an acyl phosphine oxide compound.
9. **(Previously Presented)** Coating composition according to claim 1, wherein at least one of the oxidatively drying polyunsaturated condensation products is the thiol compound, or is one of the thiol compounds.
10. **Canceled.**
11. **(Previously Presented)** Coating composition according to claim 1, wherein the ratio between the number of unsaturated groups and the number of SH-functional groups is between 2:1 and 20:1.
12. **(Previously Presented)** Coating composition according to claim 1, wherein the coating composition comprises 3-20 wt.% of thiol compounds, related to the total weight of solid resin.
13. **(Previously Presented)** Coating composition according to claim 1, wherein the coating composition is a high solids coating composition, comprising 0 – 30 wt.% solvents.
14. **(Previously Presented)** Coating composition according to claim 1, wherein the photoinitiator is a mono-, bis- or trisacyl phosphine oxide compound or a mixture thereof.
15. **(Previously Presented)** A one component coating system comprising the coating composition of claim 1.
16. **(New)** A coating composition comprising
one or more thiol compounds;
one or more oxidatively drying alkyds; and

one or more photo-initiators.

17. **(New)** A coating composition comprising:

one or more thiol compounds;

one or more oxidatively drying polyunsaturated condensation products of one or more fatty acids and/or esters, one or more polyols, optionally one or more polycarboxylic acids and/or anhydrides of polycarboxylic acids, and optionally other building blocks;

and one or more photo-initiators;

wherein the coating composition comprises more than about 70 wt % of the oxidatively drying polyunsaturated condensation products, related to the total weight of solid resin.